



Intermediate Metal Conduit

American Standard Intermediate Metal Conduit

Trade Size (in.)	Outside Diameter			Length without Coupling (mm.)	Wall Thickness (mm)	Minimum Weight of 10 Unit Lengths with Coupling, (kgs.)
	Nominal (mm.)	Minimum (mm.)	Maximum (mm.)			
1/2"	20.7	20.6	20.8	3030	1.79	25.4
3/4"	26.1	26.0	26.3	3030	1.90	34.6
1"	32.8	32.6	32.9	3025	2.16	49.9
1 1/4"	41.6	41.4	41.9	3025	2.16	64.3
1 1/2"	47.8	47.6	48.0	3025	2.29	79.1
2"	59.9	59.7	60.1	3025	2.41	105.2
2 1/2"	72.6	72.3	72.8	3010	3.56	186.2
3"	88.3	88.0	88.5	3010	3.56	229.0
3 1/2"	100.9	100.6	101.1	3005	3.56	263.0
4"	113.4	113.2	113.7	3005	3.56	296.1

TOLERANCE :

Outside Diameter

± 0.2 mm (For 1/2" - 1")
± 0.3 mm (For 1 1/4" - 2")
± 0.4 mm (For 2 1/2" - 4")

Wall Thickness

± 0.2 mm (For 1/2" - 2")
± 0.3 mm (For 2 1/2" - 4")

Length

± 6.4 mm